



LAMART CORPORATION

Flexible Laminate Solutions

Technical Data

www.lamartcorp.com

800-LAMART9

973-772-6262

PRODUCT ID: 1105-84

DESCRIPTION: **PRESSURE SENSITIVE PRODUCTS**
Products Engineered to your Specifications

CONSTRUCTION: 2 Mil High Performance Acrylic PSA on an 84# C2S
Poly-Coated kraft paper liner

BENEFITS: Hi Peel, High Shear, Moderate Tack, Acrylic PSA.
Excellent elevated Temperature Shear properties
S.A.F.T. 165°C

APPLICATION: Name Plate. Excellent for applications where higher service
temperatures are needed.

PROPERTY	VALUE			TEST METHOD
	<u>S/S</u>	<u>Aluminum</u>	<u>Glass</u>	
2 mil PET backing				PSTC 101 Method A
180° Peel Adhesion 20 min @ RT Ozs./inch	64	58	79	
24 Hrs. @ RT Ozs./inch	85	85	92	
2 mil Foil Backing Shear Adhesion ½ X 1 X 1000g Hours	<u>S/S</u>			PSTC 107 Procedure A
½ X ½ X 500g @ 70°C	>158			Procedure G
Loop Tack Lbs./in ²	2.0			PSTC 16 Method A

PN18669

Physical and performance values and characteristics shown above are obtained through recommended test procedures. The above values do not represent a guarantee of product performance and are not intended for use in determining engineering specifications. Values represent nominal and average values; individual roll values may vary from average values indicated on the datasheet. User is responsible for determining suitability and fitness for use. User assumes all risk and liability whatsoever in connection therewith. Seller assumes no liability beyond the replacement value of material.

Automotive . Aerospace . Electronics . Industrial . Medical . Printing and Graphics