



LAMART CORPORATION

Flexible Laminate Solutions

Technical Data

www.lamartcorp.com

800-LAMART9

973-772-6262

PRODUCT ID: 2105-PC61

DESCRIPTION: **PRESSURE SENSITIVE PRODUCTS**
Products Engineered to your Specifications

CONSTRUCTION: Aggressive acrylic PSA/ 0.25 ga PET Film / aggressive acrylic PSA / 61# C2S kraft paper liner.

BENEFITS: High peel, good shear, high yack, acrylic PSA. Good elevated temperature shear

APPLICATION: Corrugated splicing / manufacturing, Paper converting, high speed splicing.
Thin gauge hand-tear PET carrier film for low profile splicing, foil manufacturing

PROPERTY	VALUE			TEST METHOD
	<u>S/S</u>	<u>Aluminum</u>	Glass	
1 mil PET backing 180° Peel Adhesion				PSTC 101 Method A
	<u>Liner/ Exp</u>	<u>Liner/Exp</u>	<u>Liner/Exp</u>	
20 min @ RT Ozs./inch	111 / 112	112 / 113	113 / 117	
Shear Adhesion 1 X 1 X 1000g Hours	<u>S/S</u>			PSTC 107 Procedure A
	>100			
1 X 1 X 500g @ 70°C Hours	>24			Procedure G
Loop Tack Lbs./in ²	3.5			PSTC 16 Method A
Rolling ball tack Inches	0.25			PSTC 6
PN18927				

Physical and performance values and characteristics shown above are obtained through recommended test procedures. The above values do not represent a guarantee of product performance and are not intended for use in determining engineering specifications. Values represent nominal and average values; individual roll values may vary from average values indicated on the datasheet. User is responsible for determining suitability and fitness for use. User assumes all risk and liability whatsoever in connection therewith. Seller assumes no liability beyond the replacement value of material.

Automotive . Aerospace . Electronics . Industrial . Medical . Printing and Graphics