



LAMART CORPORATION

Flexible Laminate Solutions

Technical Data

www.lamartcorp.com

800-LAMART9

973-772-6262

Preliminary Data Sheet

PRODUCT ID: 2109-PC61

DESCRIPTION: **PRESSURE SENSITIVE PRODUCTS**
Products Engineered to your Specifications

CONSTRUCTION: 61# release liner/1.85 general purpose acrylic PSA/0.5 mil PET / 1.25 mils aggressive rubber PSA

BENEFITS: High tack, high peel, high shear, excellent general purpose Acrylic & rubber PSA's

PROPERTY	VALUE			TEST METHOD
	<u>S/S</u>	<u>Aluminum</u>	<u>Glass</u>	
180° Peel Adhesion 1 min. @ RT ozs./inch / N	125 / 35	125 / 35	115 / 32	PSTC 101 Method C
24 Hrs. @ RT ozs./inch / N	130 / 36	120 / 34	114 / 32	
Shear Adhesion 1/2 X 1 X 1000g @ RT	S/S 24 hrs.			PSTC 107 Procedure A
Loop Tack Lbs/in ²	9.0			PSTC 16 Method A

PN19041

Physical and performance values and characteristics shown above are obtained through recommended test procedures. The above values do not represent a guarantee of product performance and are not intended for use in determining engineering specifications. Values represent nominal and average values; individual roll values may vary from average values indicated on the datasheet. User is responsible for determining suitability and fitness for use. User assumes all risk and liability whatsoever in connection therewith. Seller assumes no liability beyond the replacement value of material.

Automotive . Aerospace . Electronics . Industrial . Medical . Printing and Graphics