



DATA SHEET

ELECTROSHIELD

Laminates and Coated Products Engineered
to Solve EMI/RFI Shielding Problems

PRODUCT: A-21-NPS

CONSTRUCTION: .001" aluminum foil
.00092" polyester film

APPLICATION: EMI and RFI shielding of electronic components

| <u>PROPERTY</u> | <u>VALUE</u> | <u>TEST METHOD</u> |
|----------------------|--|--------------------|
| Thickness: | .0021" | PSTC-33 |
| Peel Strength: | Not Applicable | |
| Tensile Strength: | 5,800 P.S.I. | ASTM-D-882 |
| Elongation at Break: | 75% | ASTM-D-882 |
| Color: | Silver | |
| Shelf Life: | 1 year when stored under conditions of 70 degrees F. (21 degrees C.) and 50% R.H. | |

P/N 425

rev.1: 05/10/07

Values are not intended for Engineering Specifications. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith.

Seller assumes no liability beyond the replacement value of material.

•Manufacturers of Flexible
Laminated and Coated Products.
Fabrics.

•Electrical and Electronic Shielding
and insulation Composites.

•Specialty Pressure Sensitive Tapes-
Laminates-Films, Foils, Papers,