



# LAMART CORPORATION

Flexible Laminate Solutions

## Technical Data

www.lamartcorp.com

800-LAMART9

973-772-6262

PRODUCT ID: A-35-50DK-.75

DESCRIPTION: **PRESSURE SENSITIVE PRODUCTS**  
Products Engineered to your Specifications

CONSTRUCTION: .00035" aluminum  
.003" clear polyester film with .00075" acrylic pressure sensitive adhesive and liner.

FEATURES: Laminate is extremely durable and has exceptional dimensional stability

CHEMICAL PROPERTIES: Resistant to alkalies and salt  
Fungus resistant  
Water and corrosion resistant

<u>PROPERTY</u>	<u>VALUE</u>	<u>TEST METHOD</u>
Dimensional Stability:	Excellent	
Abrasion Resistance:	Excellent	
Adhesion:	> 32 ounces/inch of width Maximum adhesion achieved after 72 hours.	ASTM-D-1000 15 minute dwell
Temperature Range:	Application temperature: 55 degrees F. minimum. Service temperature: -40 degrees F. to 250 degrees F.	
Release Value:	< 50 g/inch of width	Lamart Test Method #18
Shelf Life:	1 year when stored under conditions of 70 degrees F. (21 degrees C.) and 50% R.H.	

P/N 10393

Date 2/8/01

*Physical and performance values and characteristics shown above are obtained through recommended test procedures. The above values do not represent a guarantee of product performance and are not intended for use in determining engineering specifications. Values represent nominal and average values; individual roll values may vary from average values indicated on the datasheet. User is responsible for determining suitability and fitness for use. User assumes all risk and liability whatsoever in connection therewith. Seller assumes no liability beyond the replacement value of material.*

Automotive . Aerospace . Electronics . Industrial . Medical . Printing and Graphics